

Product Data Sheet

Redispersible emulsion powder

RDP 5 0 1 5

Cas No.: 24937-78-8

RDP 5 0 1 5 is redispersible polymer powder , also named as redispersible polymer powder, redispersible latex powder, which is a terpolymer powder of VAC/VeoVa/E ,easy dispersible in water and has good saponification resistance, and it also has a wide range of usage.

Specifications:

Appearance White powder, flow freely

Stabilizing system Polyvinyl alcohol

Additive agent Mineral Anti-block agent

Product Technical Data

Item Unit Value

Solids content $\geq 98.0\%$

Ash content (1000°C) 12 ± 2

Bulk density g/l 350-550

Average particle size μm 80~100

PH value — 5.0-8.0

MFFT(°C) approx °C 5

Tg (°C) approx °C +10

Properties

RDP 5 0 1 5 can improve adhesion, flexural strength in bending, abrasion resistance, deformability.

It has good rheology and water retention and can increase the sag resistance of tile adhesives, it can made up to tile grouts with excellent non-slump properties and putty with good properties, and more flexibility.

Special features

RDP 5 0 1 5 has no effect on rheological properties and is a low-emissions, General - purpose powder in the medium Tg range. It is eminently suitable for formulating compounds of high ultimate strength.

Application

Typical applications for RDP 5 0 1 5 :

not only for blending with inorganic binders

Hebei Yibang Building Materials Co., Ltd

Add:Jinzhou, Shijiazhuang City, China
Tel: +86-311-84442166
Email:yibanghpmc@foxmail.com
www.yibangchemical.com

The logo for EipponCell, featuring the word "EipponCell" in a bold, green, sans-serif font. The "E" and "C" are significantly larger than the other letters, and the "i" and "l" are lowercase. The logo is positioned to the right of the company contact information.

such as cement, gypsum, plaster and hydrated lime for the manufacture of thin bed mortars, plaster mortar, self-leveling mortars, wall troweling compounds, tile grouts, but also as the exclusive binder for synthetic-resin-bound systems.

Packing:

Packed in multi-ply paper bags with polyethylene inner layer, containing 25 kgs; palletized & shrink wrapped.

Storage:

Store it in a cool, dry place below 30°C and protected against humidity and pressing, since the goods is thermoplastic, storage time should not exceed 36 months.

Safety notes:

The above data is in accordance with our knowledge, but don't absolve the clients carefully checking it all immediately on receipt. To avoid the different formulation and different raw materials, please do more testing before using it.